

SEAMLESS STEEL PIPE FOR LOW TEMPERATURE SERVICE
1. Standards

EN 10216-4, ASTM A333, ASTM A334

2. Used for

Low-temperature service.

3. Dimensions

According Tab.1 and Tab.2

4. Tolerances

Standard	Outside Diameter	Wall Thickness
EN 10216-4, hot finished	$\pm 1.0\%$ or $\pm 0.5\text{mm}$ (which is higher)	$\pm 12.5\%$ or $\pm 0.4\text{mm}$ (which is higher)
EN 10216-4, cold finished	$\pm 0.5\%$ or $\pm 0.3\text{mm}$ (which is higher)	$\pm 10\%$ or $\pm 0.2\text{mm}$ (which is higher)
ASTM A333	OD \leq 48.3; +0.4/-0.8mm 48.3<OD \leq 114.3; $\pm 0.8\text{mm}$ 114.3<OD \leq 219.1; +1.6/-0.8mm OD>219.1; +2.4/-0.8mm	+12.5%/-10%
ASTM A334 , hot finished	OD \leq 100; +0.4/-0.8mm 100<OD \leq 200; +0.4/-1.2mm 200<OD \leq 225; +0.4/-1.6mm	OD \leq 100 and WT \leq 2.4; +40%/0 OD \leq 100 and 2.4<WT \leq 3.8; +35%/0 OD \leq 100 and 3.8 <WT \leq 4.6; +33%/0 OD \leq 100 and WT>4.6; +28%/0 OD>100 and 2.4<WT \leq 3.8; +35%/0 OD>100 and 3.8 <WT \leq 4.6 ; +33%/0 OD>100 and WT>4.6; +28%/0
ASTM A334 , cold finished	OD<25; +0.1/-0.1mm 25 \leq OD \leq 40; +0.15/-0.15mm 40<OD<50; +0.2/-0.2mm 50 \leq OD<65; +0.25/-0.25mm 65 \leq OD<75; +0.3/-0.3mm 75 \leq OD \leq 100; +0.38/-0.38mm	OD \leq 38.1; +20%/0 OD>38.1; +22%/0

TMK EUROPEAN DIVISION Cod: FCU-01, Ed. 3 Rev. 3/2019

 API:
5CT-0440
5L-0352

 LR:
ISO 9001
ISO 14001
ISO 45001

 TUV:
PED/AD-2000 W0/W4
TRD 100/102
Vd TUV

 TUV CPR:
EN 10210-1,2
EN 10255

 LR
DNV-GL Rules
RINA

 LR:
IATF 16949



TMK-ARTROM S.A.

Draganesti Str. 30, Slatina, jud. OLT, Romania 230119

Tel: +40 (249) 436862, 434640, 434641

Fax: +40 (249) 434330, 437288

E-mail: office.slatina@tmk-artrom.eu www.tmk-artrom.eu

EUID: ROONRC.J28/9/1991; J28/9/31.01.1991

VAT No. RO 1510210/1992

Subscribed and Paid Share Capital: 291.587.538,34 lei

	100<OD<=200; +0.38/-0.64mm	
	200<OD<=225; +0.38/-1.14mm	

5. Chemical Composition (%)

Steel group	C max	Mn max	Si max	S max	P max	Cr max	Cu max	Mo max	Ni max	Ti max	V max
P215NL	0.15	0.40÷1.20	0.35	0.020	0.025	0.30	0.30	0.08	0.30	0.04	0.02
P265NL	0.2	0.60÷1.40	0.4	0.020	0.025	0.30	0.30	0.08	0.30	0.04	0.02
Grade 6	0.30	0.29÷1.06	0.10 min	0.025	0.025						

6. Mechanical Properties

Steel group	Tensile Strength	Yield Strength min.	Elongation min.	Min. impact energy	
	MPa	MPa	%	J	°C
P215NL	360÷480	215	25	40	-40
P265NL	410÷570	265	24	40	-40
Grade 6	min. 415	240	30	18	-45

7. Lengths

Standard	Nominal Length	Min. Length		Average Length		Max. Length	
		ft	m	ft	m	ft	m
EN 10216-4, ASTM A333 & ASTM A334	20ft (6m)	16	4.88	17.5	5.33	22.5	6.86
	40ft (12m)	22	6.71	35.0	10.67	39.4	12.00

8. Protection

- unprotected;
- external varnished with black or clear lacquer;
- if required, the plain end pipes can be delivered with plastic caps at both ends.

9. Marking

According to standard or per customer request.

10. Delivery

In bundles up to 4000 kg (8800 lbs) tied in minimum six places with steel strip. Quantity tolerances: ±5% per size or / and per total.

TMK EUROPEAN DIVISION Cod: FCU-01, Ed. 3 Rev. 3/2019



API:
5CT-0440
5L-0352

LR:
ISO 9001
ISO 14001
ISO 45001

TUV:
PED/AD-2000 W0/W4
TRD 100/102
Vd TUV

TUV CPR:
EN 10210-1,2
EN 10255

LR:
DNV-GL Rules
RINA

LR:
IATF 16949



TMK-ARTROM S.A.

Draganesti Str. 30, Slatina, jud. OLT, Romania 230119

Tel: +40 (249) 436862, 434640, 434641

Fax: +40 (249) 434330, 437288

E-mail: office.slatina@tmk-artrom.eu www.tmk-artrom.eu

EUID: ROONRC.J28/9/1991; J28/9/31.01.1991

VAT No. RO 1510210/1992

Subscribed and Paid Share Capital: 291.587.538,34 lei

11. Mill test report

Mill test reports are issued to customer requirements. Usually they comply with DIN 50049, EN 10204.

12. Quality certified

LR, TUV, PED, DNV, GL.

TMK EUROPEAN DIVISION Cod: FCU-01, Ed. 3 Rev. 3/2019



API:
5CT-0440
5L-0352

LR:
ISO 9001
ISO 14001
ISO 45001

TUV:
PED/AD-2000 W0/W4
TRD 100/102
Vd TUV

TUV CPR:
EN 10210-1,2
EN 10255

LR
DNV-GL Rules
RINA

LR:
IATF 16949